

4 MINS CLEAR EPOXY

DESCRIPTION:

x'traseal® 4 MINUTES CLEAR EPOXY is a fast setting clear epoxy adhesive. It offers good gap-filling capabilities for filling defects in metal, wood and masonry and excellent strength for bonding metal to metal. After cured, it can be drilled, sanded, and painted. It contains no solvent or VOC, not flammable and no shrinkage after cure. It is very useful for emergency repairs in industries, workshops, marine, automotive, construction and also for household use.

FEATURES:

- ◆ Paintable.
- ◆ Non-shrinkage.
- ◆ Heat resistance.
- ◆ Fast setting within 4 minutes.
- ◆ Easy to use, one to one mixing ratio.
- ◆ Strong bonding strength when hardened.
- ◆ Water, solvent, acid and alkaline resistance.

USES:

- ◆ Permanent repair: Leaks, holes, cracks, mounting signs to walls.
- ◆ Suitable Substrates: Metal, fiberglass, concrete, ceramics and some plastic materials

NOT RECOMMENDED FOR:

PE, PP and PTFE.

APPLICATION:

- ◆ Surface must be clean, dry, free from oil and grease and thoroughly roughen
- ◆ Remove caps, pierce end of tubes. Squeeze equal amount of resin and hardener from each tube. Ratio 1:1.
- ◆ Mix thoroughly until homogenous.
- ◆ Apply to the surfaces to be repaired or joined together.
- ◆ Clean off excess mixture with solvent.

SPECIFICATION:

Color, Resin Hardener	Colorless Colorless
Specific gravity, Resin Hardener	1.19±0.05 g/ml 1.10±0.05 g/ml
Viscosity, Resin Hardener	13K cps 11K cps
Mixing ratio, A:B	1:1
Appearance	Liquid form
Work Life (Minutes at 25°C)	3 – 4
Curing time (Minutes at 25°C)	4 – 5
Hardness (Shore D)	Minimum 70
Temperature limits	15°C to 100°C
Nonvolatile Content	100%
Lap Shear Strength (kg/cm ²)	Minimum 50
Shelf Life	24 Months ⁽¹⁾

STORAGE:

⁽¹⁾Shelf life is subjected to change due to the type of packaging used and the condition of the environment. Material should be stored in a dry and cool place between +5°C to +30°C.

CAUTION:

Normally, while mixing by hand it does not cause any skin irritation, but in some cases with sensitive skins, it may cause irritation or sensitization. In such cases, wash the hands with plenty of water and soap and use hand gloves for application.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.

WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS