



SA-105

GP-GENERAL PURPOSE RTV
ACETIC SILICONE SEALANT

x'traseal®

TECHNICAL DATA SHEET

REV: 02

Date: 25 April 2024

DESCRIPTION

x'traseal® SA-105 general purpose RTV acetic silicone sealant is one part sealant that offer excellent adhesion, weatherability and elasticity for general glazing and for sealing application.

FEATURES

- ♦ Acetic acid curing system
- ♦ Antifungal to suit sanitary and other construction sealing applications
- ♦ Outstanding durability
- ♦ One part no mixing
- ♦ Permanently flexible
- ♦ Excellent gunnability (-20°C to 50°C)
- ♦ Weather proof
- ♦ Primerless adhesion to most materials
- ♦ UV resistance

USES

- ♦ General glazing: glass, plastic, channel or stop.
- ♦ Curtain wall sealing: glass, steel, granite and plastic.
- ♦ General sealing: sheet metal, skylights, ventilators, air-conditioning.

Due to a large variety of different coatings and substrates, we recommend preliminary compatibility tests prior to application to achieve desirable results

NOT RECOMMENDED FOR:

SA-105 is an acetic acid curing silicone and is not suitable where the acetic acid component will corrode the base material.
Not for: traffic areas or areas subject to abrasion.
Not for: structural glazing.
Not for: on marble, quartzite or natural stones.

JOINT DESIGN

The specified sealant bead size should be calculated to comply with the compression and extension capabilities of the sealant in relation to the anticipated joint width due to expansion and contraction.

Generally calculation of the width of SA-105 sealant bead should be computed on the basis of a maximum $\pm 20\%$

Compression and extension capability minimum bead size should not be less than 3mm to accommodate movement. Design joint depth of which ratio width becomes 0.5 to 1.

Suitable joint depth vs width:

6mm x 6mm
8mm x 12mm
10mm x 20mm

- * Joint size minimum 3mm x 3mm.
- * Joint size maximum 30mm.



MOHM CHEMICAL SDN. BHD. (REG NO 276851-U)
No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor,
Malaysia. Tel : +607 333 1222 Fax : +607 332 0545 / 333 7919
Website: www.xtraseal.com Email: info@mochem.com

Mohm Chemical Sdn. Bhd. is an ISO14001 & ISO9001 certified company in Malaysia. x'traseal® is a registered trademark of Mohm Chemical Sdn. Bhd. ©1993 Mohm Chemical Sdn. Bhd. All rights reserved.



SA-105

GP-GENERAL PURPOSE RTV
ACETIC SILICONE SEALANT

x'traseal®

TECHNICAL DATA SHEET

REV: 02

Date: 25 April 2024

APPLICATION

- ◆ Surface must be clean and dry.
- ◆ Mask smooth surface to simplify clean up.
- ◆ Use approved back-up material in joint.
- ◆ Cut nozzle to desired size.
- ◆ Insert cartridge into caulking gun.
- ◆ Push sealant ahead for uniform bead.
- ◆ Tool within 5 minutes.
- ◆ Clean off excess sealant with M.E.K. or toluene.

CURING TIME

SA-105 will tack free in approximately 15 minutes and will cure to a depth of 10mm in 7 days. Longer curing time may be necessary in dry and low humidity area.

SPECIFICATION

Curing system	Acetoxy
Appearance	Non-sagging paste
Odour	Vinegar smell
Specific gravity	0.95 ± 0.05
Shore A hardness	15 -21
Elongation	300%
Tensile strength	1.2MPa approx.
Tack free time	15 minutes
Application temp.	-20°C to 50°C
Service temp.	-40°C to 100°C
Shelf life	12 months

STORAGE

Material should be stored in a dry and cool place between +5°C to +30°C.

CAUTION

Read and understand material safety data sheet of this product before handling or using.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.