



N-048

NEOPRENE SEALANT

x'traseal®

TECHNICAL DATA SHEET

REV: 04

Date: 25 April 2024

DESCRIPTION

N-048 Neoprene is a one part sealer mainly consists neoprene rubber and synthetic resin. It is a special formulated sealant that cures to a tough, flexible bond to all engineering material surfaces. Because of its excellent elasticity and water resistivity, it is most suitable for water-proofing, dust-proofing and hermetically sealing of containers, cabins, bus, mobile homes and various appliances.

FEATURES

- ◆ Outstanding durability.
- ◆ One parts no mixing.
- ◆ Good adhesion and excellent elasticity to metals, woods, plastics, glass and many other engineering materials.
- ◆ 100% weather proof.
- ◆ Permanently flexible under stress to normal expansion and compression.
- ◆ Quick curing at room temperature.
- ◆ Excellent gunnability.
- ◆ Very stable properties in composite container.

USES

- ◆ For joints of containers.
- ◆ For joints of automobiles, bus and other vehicles.
- ◆ Sealing of joints in zinc roofs and slate roofs.

Due to a large variety of different coatings and substrates, we recommend preliminary compatibility tests prior to application to achieve desirable results

NOT RECOMMENDED FOR

N-048 Neoprene Sealant is not suitable for high joint movement substrate.

COLOUR

Grey. Other colours are available upon request.

APPLICATION

- ◆ Surface must be clean and dry.
- ◆ Cut nozzle to desired size.
- ◆ Insert cartridge into caulking gun.
- ◆ Push sealant ahead for uniform bead.
- ◆ Tool within 5 minutes.
- ◆ Clean off excess sealant with M.E.K. Or toluene.



N-048

NEOPRENE SEALANT

x'traseal®

TECHNICAL DATA SHEET

REV: 04

Date: 25 April 2024

SPECIFICATION

Base	Neoprene Rubber
Appearance	Non-Sagging Paste
Solvent	Aromatic Solvent Blend
Specific Gravity	1.15 ± 0.05
Solid Contents	76 ± 5%
Shore A Hardness	35 Approx.
Tensile Strength	1.2 Mpa
Tack Free Time	10 Minutes Approx.
Application Temp.	-10°C To 50°C
Service Temp.	-50°C To 100°C
Shelf Life	12 Months

STORAGE

Material should be stored in a dry and cool place between +5°C TO +30°C.

CAUTION

Highly flammable. Read and understand material safety data sheet of this product before handling or using.

This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.



MOHM CHEMICAL SDN. BHD. (REG NO 276851-U)
No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor,
Malaysia. Tel : +607 333 1222 Fax : +607 332 0545 / 333 7919
Website: www.xtraseal.com Email: info@mochem.com